



SODAL FILL & FIX FOAM

Date: 03/01/11

Page 1 of 2

Technical Data:

Base	Polyurethane
Consistency	Stable Foam
Curing System	Moisture Cure, Thixotropic
Skin Formation	Ca. 8 minutes (20°C/65% R.H.)
Drying time	Dust free after 20-25 min. at 20°C
Curing Rate	1,5h for a 30mm bead (20°C/65% R.H.)
Yield	1000mL yields 30-35L cured foam
Shrink	None
Postexpansion	None
Cellular Structure	Ca 70-80% closed cells, medium fine cellular structure
Specific Gravity	Ca. 25kg/m ³ (extruded, fully cured)
Temperature Resistance	-40°C until +90°C when cured
Colour	Champagne
Fire Class	B3 (DIN4102 part2)
Insulation Factor	33 mW/mK
Shear Strength	17 N/cm ² (DIN53427)
Pressure Strength	3 N/cm ²
Bowing Strength	7 N/cm ²
Water Absorption	1% Vol.
Acoustic Rating	R _{ST,W} =58 dB

Product:

Soudal Fill & Fix Foam with CFC-free propellant is a one-component, self-expanding, ready to use polyurethane foam with propellants which are completely harmless to the ozone layer.

Characteristics:

- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation
- Very good filling capacities
- Excellent mounting capacities
- Excellent stability (no shrink or post expansion)

Applications:

- Installation of window- and doorframes
- Filling of cavities
- Sealing of all openings in roof constructions
- Creation of a soundproof screen

- Mounting and sealing of window- and doorframes
- Connecting of insulation materials and roof constructions
- Application of a soundproofing layer on motors
- Improving thermal insulation in cooling systems
- Installation of air conditioners

Packaging:

Colour: champagne

Packaging: Aerosols can 750mL and 500mL

Shelf life and Storage:

- 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°.
- Always store can with the valve pointed upwards

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.



SOUDAL FILL & FIX FOAM

Date: 03/01/11**Page 2 of 2****Surfaces:**

Type: all substrates except PE, PP

State of Surface: clean, free of dust and grease

Preparation: Moistening of the surfaces improves adhesion and curing and results in a denser cellular structure

Application:

Shake the aerosol can for at least 20 seconds. Put the adapter on the valve. Moisten surfaces with a water sprayer prior to application. Remove pressure from the applicator to stop. Fill holes and cavities for 50 %, as the foam will expand.

Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Foam cleaner or acetone. Cured foam can only be removed mechanically. Working temperature 5°C to 35°C (20°C-25°C recommended).

Health- and Safety Recommendation:

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.
- Remove cured foam by mechanical means only, never burn away
- Consult the label for more information.

Remarks:

- Do not touch the surface during the curing time at frost temperatures
- always moisten surfaces in order to improve curing and cellular structure
- Cured PU foam must be protected from UV-radiation by painting or applying a top layer of sealants (silicone, MS Polymer, etc)
- Always store can with the valve pointed upwards.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.